

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : H01B 1/12, H01L 51/20, C08G 61/10		A1	(11) International Publication Number: WO 00/60612
			(43) International Publication Date: 12 October 2000 (12.10.00)
(21) International Application Number: PCT/GB00/01288 (22) International Filing Date: 5 April 2000 (05.04.00) (30) Priority Data: 9907802.4 6 April 1999 (06.04.99) GB (71) Applicant (for all designated States except US): CAMBRIDGE DISPLAY TECHNOLOGY LIMITED [GB/GB]; 181A Huntingdon Road, Cambridge CB3 0DJ (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): HO, Peter, Kian-Hoon [SG/GB]; 113 Histon Road, Cambridge CB4 3JD (GB). KIM, Ji-Seon [SG/GB]; 117 Mayflower House, Manhattan Drive, Cambridge CB4 1JT (GB). FRIEND, Richard, Henry [GB/GB]; 37 Barton Road, Cambridge CB3 9LG (GB). (74) Agents: SLINGSBY, Philip, Roy et al.; Page White & Farrer, 54 Doughty Street, London WC1N 2LS (GB).		(81) Designated States: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(54) Title: METHOD FOR DOPING A POLYMER			
(57) Abstract A method for forming a conjugated polymer which is doped by a dopant comprising the steps of: (a) adding a doping agent comprising a dopant moiety to a solution comprising the conjugated polymer or a precursor thereof and, optionally, a second polymer, the dopant moiety being capable of bonding to the conjugated polymer, precursor thereof or the second polymer; (b) allowing the dopant moiety to bond to the conjugated polymer, precursor thereof or the second polymer to perform doping of the conjugated polymer, characterised in that the amount of doping agent added in step (a) is less than the amount required to form a fully doped conjugated polymer.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NI	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

D scription

5

10

15

20

25

30

35

40

45

50

55

METHOD FOR DOPING A POLYMER

The present invention relates to a method for doping a conjugated polymer. Polymers preparable according to the method of the present invention are provided.

Doping of conjugated polymers (polymers with π -conjugated backbone structures and/or π -conjugated pendant groups) with strong protonic acid (p-doping) or strong oxidising (p-doping) or reducing agents (n-doping) is well established in the literature. However, the doping proceeds readily to completion in the presence of a stoichiometric or excess amount of dopants. The chemical driving force for maximum doping is very high, so that it is difficult to arrest the doping level at an intermediate value. The system achieves the *maximum* doping with about 10-50% of the conjugated repeat units doped depending on the polymer system. For poly(p-phenylenevinylenes) and polyacetylenes, this is typically 10-20%; for polythiophenes, 20-30%; for polyanilines, 40-50%. This maximum level of doping imparts a high level of electrical conductivity of the order of 1-1000 S/cm to the polymers, depending on the nature and type of the polymers and dopants used, so that they become *conducting polymers* in the process. The bulk carrier concentration is then roughly of the order of 10^{20} /cm³ to 10^{21} /cm³.

However, this high level of doping is unnecessary or even undesirable for some applications. For example, for a 1- μ m thick film (which is typical of the vertical thickness of photonic structures) having a conductivity of 10^{-6} S/cm, only a modest 1-V potential difference is required to drive a practical device current density of 10 mA/cm² through the film thickness direction. Therefore, film conductivities of the order of 10^{-6} - 10^{-2} S/cm (typical of the semiconducting range) are already sufficient for these films to be employed in semiconducting photonic structures such as distributed Bragg reflectors and waveguides.

5 Furthermore, when the films are doped to the maximum, such as
achieved by straightforward exposure to strong acids or oxidants,
10 their optical properties change in drastic ways owing to the
formation of new sub-gap transitions that change the refractive
indices of the films and cause parasitic absorption of any
emitted light. Both these factors are not desirable or
15 acceptable for photonic applications. Therefore control of the
bulk carrier concentration between 10^{17} /cm³ to 10^{20} /cm³, at an
intermediate doping-level at least about one order of magnitude
less than the maximally-doped case, is crucial.

20 Applied Physics Letters, volume 73, Number 2, pages 253-255
(1998) reports a study of the Hall mobility and the carrier
concentration of a conjugated polymer, namely polythiophene, as a
function of the electrochemical doping level. The doping level
25 of the polymer is changed by varying the oxidation potential i.e.
by potentiometric control.

30 Synthetic Metals, 68, pages 65-70 (1994) is concerned with field-
effect mobility and conductivity data obtained from two different
amorphous organic semiconductors which can be doped to a range of
different conductivities.

35 Synthetic Metals, 89, page 11-15 (1997) investigates the doping
and temperature dependence of the conductivity of poly(p)-
phenylene vinylene) (PPV).

40 Synthetic Metals, 55-57, page 3597-3602 (1993) investigates
electrical conductivity of α,α' - coupled dodecathiophene as a
function of both dopant level and time.

45 Synthetic Metals, 30, page 123-131 (1989) discloses a
relationship between acid strength and ionization potential of a
conjugated polymer that will give a highly conductive doped
50 complex.

5 Applied Physics Letters, volume 72, page 2147-2149 (1998)
describes a doped hole transporting polymer. Differing levels of
10 doping are realized by adjusting the co-evaporation rates of
polymer and dopant material.

15 The methods used to achieve different levels of doping in the
above systems are not satisfactory for controlling the doping
level to such a degree so that a balance between optical and
electrical property of the doped polymer can be struck.

20 In view of the above, there remains a need to develop a method
for preparing polymers which are doped to a controlled, low or
intermediate level which is both simple and cost effective. It
is envisaged that polymers doped to such a level will be
25 particularly useful in devices such as those referred to below in
order to avoid the disadvantages associated with polymers that
are doped to a high level. These disadvantages include intense
sub-group absorptions, changes in the optical properties of the
polymer and degradation of the photonic structure of the polymer.
30 Using polymers that are doped to a controlled, low level or
intermediate it will be possible to strike a balance between
optical and electrical properties of an organic semiconductor
when used in an optoelectronic device.
35

40 The present invention aims to provide a method for forming a
conjugated polymer that is partially doped. The present
invention further aims to provide a polymer preparable according
to the method of the present invention and uses of such polymers.

45 Accordingly, the present invention provides a method for forming
a conjugated polymer which is doped by a dopant comprising the
steps of:

50 (a) adding a doping agent comprising a dopant moiety to a
solution comprising the conjugated polymer or a precursor thereof
and, optionally, a second polymer, the dopant moiety being

5 capable of bonding to the conjugated polymer, precursor thereof
or the second polymer;

10 (b) allowing the dopant moiety to bond to the conjugated
polymer, precursor thereof or the second polymer to perform
doping of the conjugated polymer, characterised in that the
amount of doping agent added in step (a) is less than the amount
required to form a fully doped conjugated polymer.

15 The present invention further provides a conjugated polymer that
is doped to a controlled, low or intermediate level which is
preparable according to the method of the present invention.

20 The present invention still further provides a photonic device
including a polymer according to the present invention.

25 One embodiment of the present invention provides a method for
forming a partially doped polymer material, comprising: adding a
doping agent to the polymer or a precursor thereof, the doping
agent being capable of bonding to the precursor or the polymer
30 chain; and causing the doping agent to leave the precursor or the
polymer chain to form a dopant capable of doping the polymer
chain; wherein fewer moles of the doping agent are added than
would be numerically sufficient to fully dope the polymer chain.
35 Also, the present invention provides a partially doped polymer
material formed by that method. Further, the present invention
provides a device/structure (such as a photonic device) that
includes such a material.
40

The conjugated polymer or its precursor is:

45 (i) derivatised with a controlled concentration (typically
at the level less than 10-20% of the amount required for full
doping) of a dopant moiety(ies) or its(their) precursor form(s);
or

50 (ii) blended together with a polymer partner (the second
polymer), which may or may not be a conjugated polymer itself,

5 which is derivatised with such moieties to give the equivalent dopant concentration.

10 Photonic structures are then fabricated from the partially doped polymer materials, including higher-order blends and composites, containing these modified conjugated polymers by film-forming techniques. A subsequent thermal, irradiation or chemical
15 activation step may be required to generate the active dopant to dope the conjugated polymer.

20 In a first aspect of the invention, a method is provided to manipulate a precursor polyelectrolyte to give a controllable partially-doped conjugated polymer after elimination. The method involves replacement of a fraction of the counter-anions of the precursor polyelectrolyte by acid anions, such as sulfonates,
25 phosphonates, phosphates, etc, of benzene, naphthalene and other organic derivatives while the precursor polyelectrolyte is in solution. These anions are converted during thermal elimination to the corresponding strong organic acids which are less volatile and more compatible with the conjugated polymer than the
30 conventional anions, such as chloride, bromide and acetate. This leads to a higher retention of a strong acid that could favourably dope the polymer.

35 In a second aspect of the present invention, a method is provided for control over partial doping of a host conjugated polymer by blending with measured amounts of another substantially-miscible polymer (the "second polymer") which is derivatised with a small
40 fraction of dopant groups such as sulfonic acid, phosphonic acid or their precursors. The second polymer provides a means to distribute substantially homogeneously a controlled amount of dopant groups into the host conjugated polymer matrix. For this
45 to occur, the second polymer must be co-soluble in the same solvent used to deposit the desired conjugated polymer film, and preferably not undergo phase segregation in the matrix. This can
50

5 be achieved by derivatising to form a doped second polymer with a
small fraction (usually less than 50mol%) of the dopant groups.
10 If the derivatisation reaction is carried too far, the material
produced tends to be no longer soluble in the common hydrocarbon
solvents used to solubilise the conjugated polymers because of
strong interaction of the polar dopant groups.

15 In a third aspect of the present invention, a method is provided
for control over partial doping of a host conjugated polymer in
solution by derivatisation with measured amounts of the dopant
moieties, such as sulfonic acid, phosphonic acid or their
20 precursors thereby, in effect, creating a copolymer. The order
of the reaction may be inverted. Either the polymer can be
formed first and then derivatised with a small mole fraction of
the dopant; or the monomer could be derivatised first with the
25 dopant group or its precursor and then incorporated at a small
mole fraction into the primary conjugated polymer. The aim is to
distribute substantially homogeneously a controlled amount of
dopant groups into the conjugated polymer matrix.

30 The present invention will now be described in more detail with
reference to the attached drawings in which:


35 Figure 1 shows the reaction scheme according to Example 1. The
scheme is applicable to conjugated polymers that are fabricated
by thermal elimination of a cationic precursor polyelectrolyte.
An example of such a polymer is PPV. In Figure 1, X is an
40 optional alkyl or aryl spacer group, OR' and OR'' are optional
alkoxy groups, D' is a precursor dopant moiety, for example,
PO₃H⁻, SO₃⁻ or OPO₃H⁻, $y \leq 0.05$ and $n \geq 10$.

45 Figure 2a shows a polymer blend preparable according to the
reaction scheme of Example 2. Example 2 is generally applicable
to soluble conjugated polymers. Examples of such polymers
50 include alkyl- and alkoxy- derivatives of PPV, poly(fluorenes)

and their copolymers. "A" is a conjugated polymer host that is blended with "B", the second polymer, that is conjugated or non-conjugated. D is a non-precursor dopant moiety such as PO_3H_2 , SO_3H or CF_2COOH and n is as defined for figure 1.


Figure 2b shows two copolymers preparable according to the reaction scheme in Example 3. Example 3 is generally applicable to soluble conjugated polymers. Examples of such polymers include alkyl- and alkoxy- derivatives of PPV, poly(fluorenes) and their copolymers. OR' , OR'' , X, D, n and y are as defined for Figures 1 and 2a.

Figure 3 shows two reaction schemes for activating a precursor dopant moiety, D, that is (a) bonded to a second polymer in a blend or (b) part of a co-polymer system. D suitably may be SO_3H and D' suitably may be




OR' , OR'' , y, n and X are as defined for Figure 1.

Figure 4 shows a reaction scheme for activating a precursor dopant moiety D' that is part of a co-polymer system. Suitably D' may be



and D may be



OR' , OR'' , y, n and X are as defined for Figure 1.

5 Figure 5 shows a reaction scheme for activating a precursor
dopant moiety D' that is part of a co-polymer system. Suitably
D' may be SO_3R or PO_3R_2 and D may be SO_3H or PO_3H_2 . R is a leaving
10 group. OR', OR'', y, n and X are as defined for Figure 1. PAG,
a photoacid generator, suitably is a diaryliodonium salt,
triarylsulfonium salt or other onium salt.

15 Figure 6 shows an example of a polymer according to the present
invention including a dopant moiety that is a redox group.
Suitably D' may be ferrocenium or viologen. OR', OR'', X, n and
y are as defined in Figure 1.

20 Figure 7 shows schematically the energy level structure of a DBR
formed by means of partially doped conjugated polymer materials.
1a and 1b are electrodes. 2 is an emissive layer. 3a-3f are
25 polymer layers which form a "mirror structure". The HOMO and LUMO
levels of the polymer layers 3a-3f are shown.

30 The conjugated polymer according to the present invention may be
a homopolymer, copolymer, blend or composite material of
conjugated polymers. For the purposes of the present invention,
a conjugated polymer is defined as a polymer with a partially or
fully n-conjugated backbone and/or n-conjugated pendent groups.
35 The conjugated polymer after doping is preferably partially
conducting. The conjugated polymer after doping is preferably
partially semi-conducting.

40 The present invention realizes the incorporation of an amount of
dopant, or its precursor, into a polymer film, via chemical
derivatisation on the conjugated polymer chain itself or chemical
45 derivatisation on another polymer partner (the second polymer)
with which the first polymer is to be blended or copolymerised. The
second polymer may or may not be conjugated.

50 The dopant level of a polymer produced according to the present

5 method is stable and readily controllable.

10 Preferably, the amount of doping agent added in step (a) is in the range of less than 10-20%, preferably 1 to 10%, of the amount required to form a fully doped conjugated polymer. Accordingly, the polymer produced in accordance with the present method, preferably, is doped to a level of less than 10-20% compared to full or maximum doping. More preferably, the amount of doping agent added in step (a) is sufficient to form a 0.001% to 5% doped conjugated polymer. Even more preferably, the amount of doping agent added in step (a) is sufficient to form a 0.1 to 1% doped conjugated polymer. The polymer produced in accordance with the present method, preferably, will have one doped site per 10^2 - 10^4 repeat units.

25 The conductivity of the polymer after doping is suitably more than 10^{-9} S/cm and less than 1S/cm, preferably 10^{-8} S/cm to 10^{-3} S/cm, or preferably 10^{-6} to 10^{-2} S/cm. The conductivity of the polymer after doping is suitably less than 1S/cm. Preferably, the conductivity of the polymer after doping is less than 10^{-2} S/cm or 10^{-3} S/cm. It is envisaged that the conductivity of the polymer after doping also may be less than 10^{-4} S/cm or 10^{-5} S/cm. It is envisaged that the conductivity may be in the range from 10^{-9} S/cm to 10^{-13} S/cm, and preferably, in the range from 10^{-9} S/cm to 10^{-3} S/cm or 10^{-6} S/cm to 10^{-2} S/cm. The amount of dopant that is added is preferably an effective amount to achieve a conductivity in such a range.

40 In an alternative definition of a polymer preparable in accordance with the present method, the polymer is doped to a level of 10^{17} - 10^{19} cm⁻³.

45 The doping agent may bond to the precursor or polymer chain by replacing a leaving group on the chain.

50

55

5 In one embodiment of the present invention, the doping agent is a
protonic acid doping agent. Suitable dopant moieties include a
10 phosphonic acid group, a sulphonic acid group, a fluoroalkyl
carboxylic acid group or an indene carboxylic acid group.

Where the dopant moiety comprises a precursor to the dopant, the
precursor preferably comprises phosphonate or sulfonate.

15 If the dopant is incorporated in the precursor form, subsequent
activation to generate the active dopant to dope the polymer may
be necessary. This activation could be by thermal, irradiation,
20 chemical or other means. Obviously, this would be unnecessary if
the dopant is already incorporated in the active form.

25 In a further aspect of the present invention, the method also
includes a step of causing the dopant to dissociate, for example
by the application of light and/or heat. This involves cleaving
the dopant moiety from the conjugated polymer, precursor thereof
30 or the second polymer after the dopant moiety has been allowed to
bond to it in step (b). This additional step enables the dopant
to be dispersed uniformly or substantially uniformly into the
polymer matrix comprising the conjugated polymer or precursor
thereof and, optionally, the second polymer. This renders the
35 dopant substantially non-diffusing and non-volatile.

40 Where the dopant moiety bonds to a precursor of the conjugated
polymer, the method further comprises a step of forming a
conjugated polymer from the precursor thereof.

45 The step of causing the doping agent to leave the polymer chain
may be effected by heating. The step of causing the doping agent
to leave the polymer chain may result also in conjugation of the
polymer and/or formation of the polymer from the precursor.

50 Optionally, the dopant moiety may bond to the conjugated polymer,

5 precursor thereof or the second polymer in step (b) via spacer group X. Suitable spacer groups include, but are not limited to, alkyl and aryl groups.

10 The conjugated polymer according to the present invention may be any conjugated polymer and, suitably, may comprise precursor polyelectrolyte PPV or substituted PPVs. The dopant moiety
15 counterion Y may comprise a phosphonate, sulfonate, phosphate, antimonate, borate, molybdate. These counterions may form a side-chain attached to the polymer backbone when they bond to the precursor conjugated polymer.

20 Non-precursor acid dopants include (a) phosphonic acid, (b) sulfonic acid, (c) fluorocarboxyl acid groups.

25 Precursor acid dopants include (a) o-nitrobenzyl sulfonate side-chains (converting to sulfonic acid group upon irradiation), see figure 3; (b) diazonaphthaquinone sulfonate side-chains
30 (converting to indene carboxylic acid upon irradiation), see figure 4; (c) phosphonate or sulfonate ester side-chains, together with an incorporated photoacid generator (PAG) such as one of the onium salts (the onium salts generating a strong
35 protonic acid upon irradiation which cleaves the sulfonate or phosphonate ester leaving group to the corresponding acid), see figure 5. See for example, A. Reiser "Photoreactive polymers: the science and technology of resists," John Wiley & Sons, New
40 York, 1989.

45 The conjugated polymer according to the present invention may comprise poly(alkylthiophenes) and poly(alkylfluorenes) or their partners. They should be derivatised with a dopant moiety Y comprising a protonic acid group. Suitable photonic acid groups
50 include phosphonic acid, sulfonic acid, carboxylic acid or their precursor in the form of esters, anhydrides, azides, hydrazides, amides, acid chlorides. The precursor form is capable of

5 converting to the active protonic acid form under irradiation,
thermal exposure, or by reaction with another chemical agent that
10 may be originally deposited with the film or subsequently
introduced to the film. In addition, the acid group or its
precursor form could be spaced from the polymer main-chain by an
alkyl or aryl spacer and could also be attached as a separate
functional unit on the polymer chain.

15 A further class of suitable dopant moieties for use in the
present method include redox groups based on TCNQ, DDQ, TTF,
ferrocene, viologen, iron(III) chelates, or their precursors.
20 The precursor form is capable of converting to the active form
under irradiation, thermal exposure, or by reaction with another
chemical agent. These groups could also be spaced from the
polymer main chain by an alkyl or aryl spacer or attached to
25 separate functional units on the chain. The redox group could
accept electrons or donate electrons to the conjugated units,
thereby p-doping and n-doping the conjugated units, respectively.

30 Partially doped materials formed, for example, as described above
could be used to form photonic structures such as distributed
Bragg reflectors (potentially pumped reflectors), confinement
heterostructures etc. Some examples of device structures which
35 particularly advantageously may include a partially doped
conjugated polymer preparable according to the present method are
described in our co-pending UK patent application number
9815271.3, the contents of which are incorporated herein by
40 reference.

45 The photonic device may include a plurality of layers of such
doped materials, the layers alternative in their levels of
doping. The device could be a mirror, for instance a distributed
Bragg reflector.

50 A distributed Bragg reflector (DBR) consists of a stack of

5 regularly alternating higher- and lower-refractive index
dielectrics (light transmissive materials) fabricated to fulfil
the Bragg condition for reflection at particular wavelengths.
10 This occurs when the optical path of the periodicity in the
dielectric stack corresponds to half a wavelength, and the
reflectivity is further optimised when the DBR stack obeys the
equation: $\frac{1}{2} \lambda = n_1 d_1 + n_2 d_2$ and for the best performance, the DBR
15 stack obeys the equation: $\frac{1}{4} \lambda = n_1 d_1 = n_2 d_2$,
where n_1 , n_2 are the respective refractive indices; d_1 , d_2 are the
corresponding component film thicknesses in the DBR; and λ is the
desired reflection wavelength.

20 Figure 7 shows schematically the energy level structure of a DBR
formed by means of partially doped conjugated polymer materials.
The doping of the materials is controlled so that the HOMO or
25 LUMO levels (depending on whether the mirror is between the anode
or the cathode and the emissive layer) of alternate layers of the
mirror are at least approximately aligned so that the passage of
holes/electrons through the mirror is not significantly impeded
30 at the boundaries between layers of the mirror. The thicknesses
of the layers of the mirror are chosen to satisfy the conditions
for reflection. The refractive index of the layers is related to
their band gaps, but by means of partial doping the HOMO/LUMO
35 levels can be aligned independently of the band gaps.

40 Since the DBR is formed of conjugated material it could be
electrically-pumped to generate photons in addition to
reflecting.

45 The present invention will now be described by way of non-
limiting illustrative examples.

Examples

Example 1

Partial doping of poly(p-phenylenevinylene) by anion exchange of the precursor poly(p-xylylene-alpha-tetrahydrothiophene) route

This is an exemplification of the scheme outlined in Figure 1. This Example illustrates the first aspect of the present invention.

Example 1A:Preparation of partially doped PPV

To effect replacement of chloride by phenylphosphonate: 10 mL of 3 w/v% poly(p-xylylene-alpha-tetrahydrothiophenium chloride) (pre-PPV-Cl) (1.3 mmol repeat unit) dissolved in methanol is mixed with 10 mL of 20 w/v% phenylphosphonic acid (13 mmol) dissolved also in methanol. The mixture is then dialysed against pure methanol through a dialysis membrane having molecular weight cut-off of 12,000. This gives a poly(p-xylylene-alpha-tetrahydrothiophenium phenylphosphonate) precursor (pre-PPV-PA) polymer which is retained by the dialysis membrane. The retentate can then be concentrated to the desired concentration and blended with the parent poly(p-xylylene-alpha-tetrahydrothiophenium chloride) in the desired ratio for solution casting. This allows control over the level of doping in the final product.

To analyse the material:

(1) A small volume of the methanol solution pre-PPV-PA was evaporated to give a white solid. Thermogravimetry experiments under nitrogen show this material exhibits a weight loss step extending from 150°C to about 300°C. This occurs over a wider range than for the parent poly(p-xylylene-alpha-tetrahydrothiophenium chloride) material which exhibits a weight loss step ending at about 200°C. This is despite the fact that phenylphosphonate, being a better leaving group than chloride, undergoes slow elimination from the PPV backbone even at room

5 temperature. The greater thermal stability in thermogravimetry experiments is therefore due to the considerably lower vapour pressure (and hence smaller evaporation loss) of phenylphosphonic

10 acid. This confirms that greater retention of the phenylphosphonic acid occurs for the same temperature.

15 2) The pre-PPV-PA material in methanol is spin-cast onto glass substrates and then baked at 180°C under vacuum for 2 hours to effect conversion to the conjugated PPV. X-ray photoelectron spectroscopy confirms a significant retention of the PA: 7 mol% (relative to PPV repeat unit) retention of the PA compared to less than 0.5 mol% retention of Cl in the parent material.

20 (3) Photothermal deflection spectroscopy of a film of a precursor PPV counterbalanced by 10 mol% PA + 90 mol% Cl (made by blending) shows sub-gap absorption strength of 60 cm⁻¹ at 750-nm wavelength. This corresponds to a doping level (that is, the ratio of ionized dopant-to-PPV repeat unit) of 0.1 mol% - 0.01 mol%.

30 Example 1 B:

Diode structure including partially doped PPV

35 To demonstrate the improvement in electrical conductivity associated with partial doping according to the present invention diode structures with indium-tin oxide/poly(3,4-dioxythiophene):poly(4-styrenesulfonate) composite anodes and calcium cathodes were fabricated for active layers (i) and (ii) defined in Table 1.

Table 1

Device structure	Drive voltage required to achieve current density of $1\mu\text{A}/\text{cm}^2$	Drive voltage required to achieve current density of $10\mu\text{A}/\text{cm}^2$
(i) Undoped 69-nm-thick PPV film with 50 vol% silica	5.0 V	7 V
(ii) Partially-doped PPV stack having a combined thickness of 207 nm for the films with 50 vol% silica and 171 nm for the neat films, and with an addition 105-nm-thick emitter polymer film	5.0 V	10 V

For the structure(i) with the undoped PPV polymer (dispersed with silica particles to change its refractive index), a large voltage is required to drive currents through a thin film of the material owing to the additional resistance offered by the silica particles. For the structure (ii) with the partially-doped PPV however, the resistance is clearly reduced by a considerable amount. Similar drive voltages can deliver comparable current densities through much thicker combined polymer film thickness. In the absence of doping, the required voltage is expected to increase as the square of the film thickness so that more than 50 V will be needed for $1\mu\text{A}/\text{cm}^2$ in structure (ii).

At the same time, no deleterious absorptions in the sub-gap spectral region of the PPV occurs. This allows the material to be used in transmissive photonic structures.

Example 2:

Partial doping of organic-soluble poly(p-phenylenevinylene) and poly(fluorene) derivatives by blending with a second polymer bearing a small fraction of dopant acid groups

This is an exemplification of the scheme in Figure 2a.

5 Example 2A:Preparation of partially doped PPV and polyfluorene

10 Poly(styrenesulfonic acid-co-styrene) copolymer (PSSH-co-PS) as the "second polymer" is blended in [alkoxyphenyl-PPV]-co-[dialkoxyl-PPV] (P1) or poly(dialkylfluorene-co-triarylamine) (P2) as host.

15 This illustrates the generality of the second aspect of the present invention.

20 To prepare the PSSH-co-PS: 0.5 g of polystyrene (4.8 mmol repeat unit) is dissolved with heating into 5 mL anhydrous chloroform in a borosilicate glass reaction flask sealed with teflon-faced silicone rubber septa, and the mixture cooled to -8°C in a bath of calcium chloride and ice-water. 0.01 mL of chlorosulfonic acid (0.15 mmol) is dissolved into 2 mL of chloroform and then syringed into the PS polymer solution. A white cloudy mixture develops almost immediately. The mixture is warmed to room temperature after 30 minutes and 3 mL of water is added, and the mixture optionally refluxed. To work up, 40 mL of toluene is added and the white precipitate is washed and isolated twice by centrifuge. The precipitate is then purified by dissolving in tetrahydrofuran and re-precipitation from toluene. This material is insoluble in chloroform, methanol or toluene, but soluble in tetrahydrofuran from which good quality films can be cast.

40 The difference Fourier-transform infrared spectrum of a thin film of the PSSH-co-PS cast on silicon substrates shows the asymmetric and symmetric S-O sulfonate bands at 1000-1200 cm⁻¹ and the appearance of the 2-adjacent hydrogen wagging vibration at 840-860 cm⁻¹. This confirms successful sulfonation of PSSH-co-PS with an expected 1-2 mol% of PSSH. Increasing the PSSH content to 50 mol% leads to an intractable material that is insoluble in common solvents. Increasing the PSSH content further to near 100 mol% gives a material that is soluble in water and methanol. The

PSSH-co-PS with a low PSSH content less than 10 mol% is therefore compatible with a range of conjugated polymers, and so can be used to regulate the level of doping in these materials.

Example 2B:

A diode structure including a partially doped PPV or polyfluorene

To demonstrate that the PSSH-co-PS material with 2 mol% PSSH can be used to improve the electrical conductivity of the conjugated polymer host, we fabricated diode structures with indium-tin oxide anodes and aluminium cathodes for the following active layers. The drive voltages for the selected diode current densities are shown in Table 2.

Table 2

Device structure	Drive voltage required to achieve current density of $1\mu\text{A}/\text{cm}^2$	Drive voltage required to achieve current density of $100\mu\text{A}/\text{cm}^2$
(i) Undoped 1.05- μm -thick P1 film	5.5 V	47 V
(ii) Partially-doped 1.05- μm -thick P1 film with 1 w/w% of PSSH-co-PS	2.0 V	33 V
(iii) Partially-doped 1.05- μm -thick P1 film with 10 w/w% of PSSH-co-PS	1.1 V	9 V
(iv) Undoped 1.65- μm -thick P2 film	9.5 V	40 V
(v) Partially-doped 1.65- μm -thick P2 film with 1 w/w% of PSSH-co-PS	5.5 V	25 V

For devices with the 1.05- μm -thick P1 polymer film (that is, structures (i)-(iii)), a substantial reduction in drive voltage, for example from 47 V to 9 V at $100\mu\text{A}/\text{cm}^2$, is achieved upon doping with 10 w/w% of the PSSH-co-PS. At the same time, there is no significant loss of transmission (less than 1% transmission loss) in the sub-gap spectral region of the host polymer. This is because the ratio of PSSH dopant-to-polymer repeat unit is

5 about 0.5 mol%, and the actual doping level (that is, the ratio of ionized PSSH-to-repeat unit) could be even lower depending on the ionization potential of the polymer.

10 For devices with the 1.65- μm -thick P2 polymer (that is, structures (iv) and (v)), a similar reduction is observed, from 40 V to 25 V at 100 $\mu\text{A}/\text{cm}^2$, upon doping with 1 w/w% of the PSSH-co-PS. In this case, doping with 10 w/w% of the PSSH-co-PS gives
15 phase separation as evident by cloudy nature of the deposited films.

20 These examples demonstrate the use of partially-derivatised polymeric dopants in a blend to regulate the doping-level and hence improve the electrical conductivity of conjugated polymer films for photonic structures.

25 Example 3:

Partial doping of an organic-soluble poly(fluorene) derivative by partial derivatisation with a small fraction of acid groups

30 This is an exemplification of the scheme outlined in Figure 2b.

35 Example 3A:

Preparation of a partially doped poly(fluorene)

40 In this example, the synthesis and use of a partially sulfonated poly(fluorene-co-triphenylamine) (SP2: S denotes sulfonation) is used to illustrate the generality of the third aspect of the present invention.

45 To prepare the SP2-co-P2: 0.1 g of P2 (0.25 mmol fluorene repeat unit) is dissolved into 5 ml of anhydrous chloroform in a borosilicate glass reaction flask sealed with teflon-faced silicone rubber septa, and the mixture cooled to -8°C in a bath
50 of calcium chloride and ice-water. Chlorosulfonic acid is

dissolved into chloroform to give an equivalent of 0.0025 ml of chlorosulfonic acid (0.037 mmol) per ml of chloroform. 1 mL of this solution is then syringed into the P2 polymer solution. An orange solution is obtained almost immediately. The mixture is warmed to room temperature after 30 minutes, and 40 mL of acetone is then added to produce a white precipitate. The precipitate is recovered by centrifugation and then purified by dissolving in chloroform and re-precipitating from methanol. This SP2-co-P2 material is soluble in chloroform, toluene and tetrahydrofuran but insoluble in methanol and acetone.

The difference Fourier-transform infrared spectrum of a thin film of the SP2-co-P2 material cast on silicon substrates shows (i) the asymmetric and symmetric S-O sulfonic bands at 1355 cm^{-1} and 1175 cm^{-1} respectively, (ii) the S-O band at 905 cm^{-1} , (iii) the appearance of the one-hydrogen wagging vibration at $860\text{--}880\text{ cm}^{-1}$. This confirms sulfonation of SP2-co-P2 with an expected 5-10 mol% of sulfonic acid groups.

To demonstrate that this derivatised material has a better electrical conductivity than its parent, we fabricated diode structures with indium-tin oxide anodes and aluminium cathodes for the following active layers. The drive voltages for selected diode current densities are shown in Table 3.

Table 3

Device structure	Drive voltage for current density of $1\mu\text{A}/\text{cm}^2$	Drive voltage for current density of $100\mu\text{A}/\text{cm}^2$
(i) Undoped 1.1- μm -thick P2 film	10.5 V	31 V
(ii) Partially-doped 1.1- μm -thick P2 film with 1 w/w% of SP2-co-P2	4.5 V	21 V

A significant reduction in drive voltage, for example from 31 V to 21 V at $100\text{ }\mu\text{A}/\text{cm}^2$ in 1.1- μm -thick films, is obtained in the

5 presence of partial doping by an equivalent of 0.05 mol% - 0.1
mol% of sulfonic acid groups. At the same time, there is no
10 significant loss of transmission in the sub-gap spectral region
of this P2 polymer.

15 This example therefore demonstrates the use of a controlled level
of dopant derivatisation of the conjugated polymer to improve the
electrical conductivity of conjugated polymer films for use in
photonic structures.

20 Example 4:

Examples 2 and 3 were repeated but with the sulfonic acid polymer
subsequently reacted with quantitative amounts of o-
25 nitrobenzylbromide in chloroform or tetrahydrofuran before film
formation to give the o-nitrobenzylsulfonate ester as the
precursor dopant. The polymer was then blended with the host
polymer as in Example 2 or used neat (similar to Example 3) in a
suitable solvent and formed into a film. The precursor sulfonate
30 ester group was then cleaved by UV exposure to generate the
active sulfonic acid group in the film.

35 Example 5:

Examples 2 and 3 were repeated but with the sulfonic acid polymer
subsequently reacted with excess of methylating agent such as
40 diethylsulfate before film formation to give the methylsulfonate
ester as the precursor dopant. The polymer was then blended with
small quantities of a photoacid generator such as
diphenyliodonium chloride or other diaryliodonium,
45 triarylsulfonium or other onium salts, and further optionally
blended with the host polymer (such as in Example 2) or used
substantially neat (similar to Example 3) in a suitable solvent
and formed into a film. The polymer film was then exposed to
50 light or heat to cleave the photoacid generator to produce a

5 strong acid with then cleaves the sulfonate ester to the active
sulfonic acid.

10 The present invention is not limited to the examples described
above.

15 The applicant draws attention to the fact that the present
invention may include any feature or combination of features
disclosed herein either implicitly or explicitly or any
generalisation thereof, without limitation to the scope of any of
20 the present claims. In view of the foregoing description it will
be evident to a person skilled in the art that various
modifications may be made within the scope of the invention.

25

30

35

40

45

50

55

Claims

5

10

15

20

25

30

35

40

45

50

55

CLAIMS:

1. A method for forming a conjugated polymer which is doped by a dopant comprising the steps of:

(a) adding a doping agent comprising a dopant moiety to a solution comprising the conjugated polymer or a precursor thereof and, optionally, a second polymer, the dopant moiety being capable of bonding to the conjugated polymer, precursor thereof or the second polymer;

(b) allowing the dopant moiety to bond to the conjugated polymer, precursor thereof or the second polymer to perform doping of the conjugated polymer;

characterised in that the amount of doping agent added in step (a) is less than the amount required to form a fully doped conjugated polymer.

2. A method according to claim 1, wherein the amount of doping agent added in step (a) is in the range of less than 10-20% of the amount required to form a fully doped conjugated polymer.

3. A method according to claim 1 or claim 2, wherein the amount of doping agent added in step (a) is sufficient to form a 0.1% to 5% doped conjugated polymer.

4. A method according to claim 3, wherein the amount of doping agent added in step (a) is sufficient to form a 1% doped conjugated polymer.

5. A method according to any one of the preceding claims, wherein the doping agent is a protonic acid doping agent.

6. A method according to claim 5, wherein the dopant moiety is selected from the group consisting of a phosphonic acid group, a sulfonic acid group, a fluoroalkyl carboxylic acid group or an indene carboxylic acid group.

5 7. A method according to any one of claims 1 to 5, wherein the dopant moiety comprises a precursor to the dopant.

10 8. A method according to claim 7, wherein the precursor dopant moiety comprises phosphonate or sulfonate.

15 9. A method according to claim 8, wherein step (c) includes heating the dopant moiety to generate the dopant.

20 10. A method according to any of the preceding claims, wherein step (b) includes cleaving the dopant moiety from the conjugated polymer, precursor thereof or the second polymer.

25 11. A method according to claim 10, wherein the dopant moiety is cleaved from the intermediate polymer by heating.

30 12. A method according to any one of the preceding claims, wherein the dopant moiety bonds to the conjugated polymer, precursor thereof or the second polymer in step (b) via a spacer group.


35 13. A method according to any one of the preceding claims, further including a step of forming a conjugated polymer from the precursor thereof.

40 14. A method according to claim 13, wherein the precursor of the conjugated polymer comprises a substituted precursor polyelectrolyte PPV.


45 15. A method according to any one of the preceding claims, wherein the conjugated polymer comprises substituted or unsubstituted PPV.

50 16. A method according to claim 14 or claim 15, wherein the conjugated polymer comprises the structure shown in formula I or

II:



(I)



(II)

where Y is the dopant moiety; OR' and OR'' are each an alkoxy group or H; X is an alkyl or aryl spacer group or a direct bond; $y \leq 0.05$ and $n \geq 10$.

17. A method according to any one of the preceding claims, wherein the second polymer is co-polymerised with the conjugated polymer or precursor thereof prior to adding the doping agent in step (a).

18. A method according to any one of claims 1 to 16, wherein the second polymer is blended with the conjugated polymer or precursor thereof prior to adding the doping agent in step (a).

19. A method according to claim 18, wherein the second polymer comprises substituted or unsubstituted PPV.

20. A method for forming a partially doped polymer comprising the steps of:

(a) adding a doping agent to the polymer or a precursor

5 thereof, the doping agent being capable of bonding to the precursor or the polymer; and

10 (b) causing the doping agent to leave the precursor or the polymer to form a dopant capable of doping the polymer;

wherein fewer moles of the doping agent are added than would be numerically sufficient to fully dope the polymer chain.

15 21. A method according to any one of the preceding claims, additionally comprising the step of:

(d) causing the dopant to dissociate to form a substantially uniformly doped conjugated polymer.

20 22. A method according to any one of the preceding claims, additionally comprising the step of processing the solution to form a film layer.

25 23. A doped conjugated polymer preparable by the method as defined in any one of claims 1 to 22.

30 24. A polymer according to claim 23, wherein the doped conjugated polymer has a conductivity of more than 10^{-3} S/cm and less than 1S/cm.

35 25. A polymer according to claim 24, wherein the doped conjugated polymer has a conductivity of from 10^{-8} S/cm to 10^{-3} S/cm.

40 26. Use of a polymer as defined in any one of claims 23 to 25, as a light emissive material.

45 27. A photonic device comprising a polymer as defined in any one of claims 23 to 25.

50 28. A photonic device according to claim 27, comprising a distributed Bragg reflector.

5

29. An optical device comprising a polymer as defined in any one of claims 23 to 25.

10

15

20

25

30

35

40

45

50

55




FIGURE 1




FIGURE 2a




FIGURE 2b

3/6




FIGURE 3a




FIGURE 3b




FIGURE 4




FIGURE 5




FIGURE 6




FIGURE 7

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 H01B1/12 H01L51/20 C08G61/10		International Application No PCT/GB 00/01288
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 H01B H01L		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, PAJ, INSPEC		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 00 04593 A (TESSLER NIR ;HO PETER (GB); CAMBRIDGE DISPLAY TECH (GB); FRIEND RI) 27 January 2000 (2000-01-27) page 11, line 1-22 page 29, line 27 -page 35, line 23	1-29
A	US 4 222 903 A (MACDIARMID ALAN G ET AL) 16 September 1980 (1980-09-16) the whole document --- -/-	1,20
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "Z" document member of the same patent family		
Date of the actual completion of the international search 27 July 2000		Date of mailing of the international search report 03/08/2000
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. J1 651 epo.nl Fax: (+31-70) 340-3018		Authorized officer De Laere, A

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Int. onal Application No
PCT/GB 00/01288

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>C.C. HAN ET AL: "Protonic acids: generally applicable dopants for conducting polymers" SYNTHETIC METALS, vol. 30, 1989, pages 123-131, XP000924913 LAUSANNE, CH ISSN: 0379-6779 cited in the application the whole document -----</p>	1,20

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/GB 00/01288

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 0004593 A	27-01-2000	AU 4921499 A	07-02-2000
US 4222903 A	16-09-1980	NONE	